

## TECHNICAL INFORMATION

### Valéron® Synthetic Paper - Uncoated

Valéron® Synthetic Paper is a multi-layer product comprised of thin individual layers of high density polyethylene (HDPE) that have been extruded, stretched, bias-cut and cross laminated into a composite structure comprised of three to fifteen total layers. The end result is a unique polyolefin sheet or “plastic plywood” that is extremely tough, tear resistant and completely waterproof. Unaffected by most chemicals, it has a wide service temperature range and is formulated to provide extended outdoor performance. It is non-toxic, odorless and can be recycled or incinerated.

Uncoated (UCT) Valéron® Synthetic Paper is corona treated on both sides during the final stage of manufacturing. The treating process, which is not a coating, allows inks, adhesives and top coats to adhere to otherwise unreceptive plastic by oxidizing the surface layers of the sheet as it passes under corona arcing. The dyne level at the time of shipment is typically in the 42-46 range, with little to no decay expected for up to twelve months under normal storage conditions.

Refer to additional Pressure Sensitive Adhesive (PSA)\* Technical Data Sheets where applicable.

### PRODUCT NUMBER - VL 6500 6.5 mil UCT Valéron®

TYPICAL PROPERTIES	UNITS	VALUE	TEST METHOD
Nominal Gauge - Average	Mils	6.5	Continuous Gauging
Yield	Sq.In./Lb. Lbs./MMSI	4,747 211	Approximate
Basis Weight - 25" x 38" x 500	Lbs./Ream	100.1	Approximate
Tensile Strength At Break - MD/TD Average	Lbs./1" Width PSI	42 6,470	ASTM D-882
Elongation At Break - Minimum	%	100	ASTM D-882
Toyo Impact - Spherical Head	Kg./Cm.	200	ASTM D-781
Puncture-Propagation Tear Resistance	Grams	6,500	ASTM D-2582
Initiated Tear Propagation - Tongue Tear	Lbs.	9.4	ASTM D-1938
Uninitiated Tear Resistance - Graves Tear	Lbs.	13.4	ASTM D-1004
Service Temperature Range	<sup>0</sup> F.	-70 to +200	
Surface Treatment	Dynes/Sq.Cm.	42 Minimum	
Primary Print Surface	Rolls: PPS “Wound-In”	Sheets: PPS “Face-Up”	
FDA Status	Title 21,CFR177.1520 Compliant For Direct Food Contact		

The information contained herein is to the best of our knowledge true and accurate. Nothing contained herein is to be construed as a recommendation to use any product in conflict with any patent. Purchaser should confirm product compatibility prior to use since CONVERT-ALL, INC. MAKES NO WARRANTIES AS TO THE FITNESS OR MERCHANTABILITY OF ANY PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations, and disclaims all liability for resulting loss or damage. Valéron® is a registered trademark of ITW. \*Sold under our PrintMaster® product line. PrintMaster® is a registered trademark of Convert-all, Inc.